


# 小麦川砕石（株）【再生砕石 RC-40 製造フロー】





①RC-30



②RC(40~20)



③RC(20~13)



④RC(13~5)



RC-30



RC(40~20)



⑤RC(0~5)

②RC(40~20)に  
①③④⑤を加えて  
RC-40 (Co100%) を製造

RC-40とC-40を  
1対1で混合・攪拌

新材碎石 (C-40)

再生碎石 RC-40  
Co:50%  
新材:50%

混合・攪拌



タイヤショベルでRC-40とC-40を  
1対1で計量混合・攪拌



製品 再生碎石 RC-40

製品の使用状況



・石垣・擁壁の裏込め材



・道路の路盤材



・建築物の基礎材